


华亚东营塑胶有限公司

产品检验报告/质量合格证

编号：HYDY/JLA-C05/015072903AD-A

第 1 页 / 共 1 页

委托单位	华亚东营塑胶有限公司生产一课	品牌	南亚牌	标志																																																																	
样品名称	PVC-U 给水管	规格型号	110mm×2.7mm																																																																		
样品编号	015072903AD-A	样品状态	颜色为灰色、外表光滑、截面平整无缺陷，数量满足试验要求																																																																		
生产日期	2015.07.23~2015.07.29	收样日期	2015.07.29																																																																		
检验日期	2015.07.30~2015.08.01	检验依据	GB/T 10002.1-2006																																																																		
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 20%;">检验项目</th> <th style="width: 20%;">技术指标</th> <th style="width: 40%;">检验结果</th> <th style="width: 20%;">单项判定</th> </tr> </thead> <tbody> <tr> <td>外观</td> <td>无缺陷</td> <td>视其外观无缺陷</td> <td>合格</td> </tr> <tr> <td>颜色</td> <td>灰色</td> <td>灰色</td> <td>合格</td> </tr> <tr> <td>平均外径mm</td> <td>110.0~110.4</td> <td>110.2</td> <td>合格</td> </tr> <tr> <td>壁厚mm</td> <td>2.7~3.2</td> <td>2.7</td> <td>合格</td> </tr> <tr> <td>不圆度mm</td> <td>≤2.2</td> <td>0.3</td> <td>合格</td> </tr> <tr> <td>弯曲度%</td> <td>≤1.0</td> <td>0.1</td> <td>合格</td> </tr> <tr> <td>长度 mm</td> <td>≥4000</td> <td>4020</td> <td>合格</td> </tr> <tr> <td>承口中部内径 mm</td> <td>110.1~110.4</td> <td>110.3</td> <td>合格</td> </tr> <tr> <td>承口最小深度 mm</td> <td>≥61.0</td> <td>125.0</td> <td>合格</td> </tr> <tr> <td>承口壁厚 mm</td> <td>≥2.0</td> <td>2.1</td> <td>合格</td> </tr> <tr> <td>水压试验 (20℃、诱导应力 38MPa)</td> <td>持压 1h 无破裂、无渗漏</td> <td>1.90MPa 持压 1h 无破裂、无渗漏</td> <td>合格</td> </tr> <tr> <td>落锤冲击试验 (0±2℃) TIR %</td> <td>≤5</td> <td>冲击 50 次均无破裂</td> <td>合格</td> </tr> <tr> <td>纵向回缩率 %</td> <td>≤5</td> <td>1.4</td> <td>合格</td> </tr> <tr> <td>倒角</td> <td>15° / 厚度≥1.4mm</td> <td>15° / 1.5</td> <td>合格</td> </tr> <tr> <td>不透光性</td> <td>不透光</td> <td>不透光</td> <td>合格</td> </tr> </tbody> </table>						检验项目	技术指标	检验结果	单项判定	外观	无缺陷	视其外观无缺陷	合格	颜色	灰色	灰色	合格	平均外径mm	110.0~110.4	110.2	合格	壁厚mm	2.7~3.2	2.7	合格	不圆度mm	≤2.2	0.3	合格	弯曲度%	≤1.0	0.1	合格	长度 mm	≥4000	4020	合格	承口中部内径 mm	110.1~110.4	110.3	合格	承口最小深度 mm	≥61.0	125.0	合格	承口壁厚 mm	≥2.0	2.1	合格	水压试验 (20℃、诱导应力 38MPa)	持压 1h 无破裂、无渗漏	1.90MPa 持压 1h 无破裂、无渗漏	合格	落锤冲击试验 (0±2℃) TIR %	≤5	冲击 50 次均无破裂	合格	纵向回缩率 %	≤5	1.4	合格	倒角	15° / 厚度≥1.4mm	15° / 1.5	合格	不透光性	不透光	不透光	合格
检验项目	技术指标	检验结果	单项判定																																																																		
外观	无缺陷	视其外观无缺陷	合格																																																																		
颜色	灰色	灰色	合格																																																																		
平均外径mm	110.0~110.4	110.2	合格																																																																		
壁厚mm	2.7~3.2	2.7	合格																																																																		
不圆度mm	≤2.2	0.3	合格																																																																		
弯曲度%	≤1.0	0.1	合格																																																																		
长度 mm	≥4000	4020	合格																																																																		
承口中部内径 mm	110.1~110.4	110.3	合格																																																																		
承口最小深度 mm	≥61.0	125.0	合格																																																																		
承口壁厚 mm	≥2.0	2.1	合格																																																																		
水压试验 (20℃、诱导应力 38MPa)	持压 1h 无破裂、无渗漏	1.90MPa 持压 1h 无破裂、无渗漏	合格																																																																		
落锤冲击试验 (0±2℃) TIR %	≤5	冲击 50 次均无破裂	合格																																																																		
纵向回缩率 %	≤5	1.4	合格																																																																		
倒角	15° / 厚度≥1.4mm	15° / 1.5	合格																																																																		
不透光性	不透光	不透光	合格																																																																		
总判定																																																																					

批准： 

审核： 

编制： 检验员01

地址：山东省东营市东二路 251 号
 电话：0546-8305238
 邮政编码：257091

传真：0546-8307178
 E-mail: huaya@hydyplst.com.cn
 http://www.hydyplst.com.cn